

As of: May 20, 2022

GENERAL INFORMATION				
Product group	GRP LINER sewage			
Product range	SAERTEX-LINER® ENVIRONMENT			
Design	Type S+			
Utilization	Municipal wastewater, rainwater, combined sewage			
Reinforcing material	Multiaxial fabric made of glass fiber			
Resin type	Styrene-free vinyl ester resin (SFVE)			
Impregnation	Pre-impregnated at the factory			
Curing procedure	Light-cured pipe lining (UV-CIPP)			
Installation procedure	Pull in place			
Inflation procedure	Compressed air			
Shelf life	DN	Composite wall thickness	Transport conditions	Storage stability
	150 - 1200	3 – 9 mm	Temperature control required	6 months 7 to 18°C
	1201 - 1500	9 – 12 mm	Temperature control required	3 months 7 to 14°C
Pressure table	Available			
EC Safety Data Sheet	Available			

DESIGN CHARACTERISTICS			
Maximum operating pressure (MDP)	Gravity pipeline		up to 1 bar/up to 14 psi
Host pipe profile	All types		Circular
Diameter range	DN 150-1500/6" – 60"		DN 250-1200/10" – 48"
Structural wall thickness	3 mm-12mm, in 1 mm increments		4 mm-12mm, in 1 mm increments
Permissible elongation	≤400: DN + 2% >400: DN + 4%		On request
Inner foils with barrier function**	Standard	FastPlus*	Pressure
Outer foils**	Integrated gliding foil with UV light protection and permanent foil with barrier function		
Material characteristics group according to DWA M 144-3	19		
Liner construction as outlined in:	DIBt approval Z-42.3-350, Annex 1 and 2, abZ/AB		

* FastPlus available for DN 200 to DN 1500/8"-60" diameter, max wall thickness 12 mm

** Details see section "FOILS"

As of: May 20, 2022

FOILS			
Inner foils with barrier function	Standard	FastPlus*	Pressure
- Remains in the liner	Temporary	Semi-permanent	Permanent
- Materials	PE/PA	PE/PA, nonwoven PET	PE/PA, nonwoven PET
- Thickness	Up to 200 µm	Up to 400 µm	Up to 400 µm
Protective outer gliding foil, UV light protection*, integrated			
- Material	PVC, fabric reinforced in places		
- Thickness	Up to 500 µm		
Permanent outer foil with barrier function			
- Material	PE/PA/PE and nonwoven PP		
- Thickness	Up to 200 µm		

*Up to DN 600/24 inch and max. 2.5 t liner weight and corresponding condition of host pipe installation possible without additional gliding foil.

Notes (terms ISO 11296- 4):

- Temporary: Foil is removed after curing.
- Semi-permanent: Facilitates liner installation and curing without post-installation functions. Remains in the liner.
- Permanent: Facilitates liner installation and curing with post-installation functions. Remains in the liner.

MECHANICAL CHARACTERISTICS	
Short-term circumferential E modulus according to DIN EN 1228	≥ 12.950 N/mm ² : 1,878,235 psi
Short-term bending E modulus according to DIN EN ISO 11296-4 // DIN EN ISO 178	≥ 15.000 N/mm ² : 2,175,565 psi
Short-term bending stress according to DIN EN ISO 11296-4 // DIN EN ISO 178	≥ 230 N/mm ² : 33,355 psi
Long-term circumferential E modulus* _{ex 50 years} according to DIN EN 761	9.300 N/mm ² : 1,370,605 psi
Long-term bending stress E modulus* _{ex 50 years} according to DIN EN 761	165 N/mm ² : 23,930 psi
Retention factor A after 2,000 hours* according to DIN EN 761	1.39/72%
Creep tendency after 24 hours according to DIN EN ISO 899-2	≤ 6 %

* These values are used for the static calculation of the liner's stability according to DWA-A 143-2.
Preliminary values after 2,000 h test.

As of: May 20, 2022

COMPOSITE REINFORCEMENT	
Glass fiber type according to DIN 61850	Permanently corrosion and chemical resistant, ECR
Number of layers multiaxial fabric	at least 2
Glass area weight per mm wall thickness	1100 g/m ² ± 150 g/m ²
Specific density according to DIN EN ISO 1183-2	1.6 g/cm ³ ± 0.5 g/cm ³
Glass content according to DIN EN ISO 1172	≥ 49% (mass-based)
Barcol hardness according to DIN EN 59	≥ 50 IRHD
Longitudinal seam	Yes
Winding	No